

## High-Performance Polyolefin and Styrenic Compounds for Extrusion and Thermoforming Applications



## A Premium Surface Finish

Enhanced polyolefin and styrenic compounds from LyondellBasell offer high-quality appearance and performance for your surface needs. Our innovative solutions enable paintable and paint-free applications that look as good as they last – even in harsh outdoor environments. And last they will, with fade-resistant color retention and stain resistance, combined with a strength that goes right through to the core.

The flexibility and the versatility of these remarkable materials make them a cost-effective replacement for many traditional materials, allowing you to differentiate and customize your applications.

## The Secret Is in the Science

These weatherable polymers are the future of surface finish technology and an innovative approach to Class “A” decorative surfaces. This patented thermoplastic olefin technology is suitable for a variety of processes, including thermoforming, film and sheet extrusion, and profile extrusion. Parts formed from these resins exhibit high resistance to bubbling, chipping, staining and fading and provide superior color and product protection.

These materials are based on TPO, ASA, ASA/PC and ASA/AES polymers and offer a broad range of engineered properties that can be customized for your unique application needs. They offer exceptional UV resistance, lasting durability, extreme toughness, paintability and excellent color retention, and they are available in a broad range of gloss levels and custom colors.

## Your Materials of Choice

LyondellBasell’s polyolefin and styrenic compounds offer superior advantages over conventional materials including painted metal or plastic, laminated paint films, acrylic laminates and coatings:

- High-quality appearance with mold-in-color technology and paintable applications for class “A” finishes
- Improved resistance to chipping and scratching across a variety of outdoor environments and high-stretch thermoforming processes
- Process versatility
- Customized color and color-matching
- Cost-effective performance
- Extrusion and Thermoforming scrap can be re-extruded / (re-processed)



## Enhanced Polyolefin and Styrenic Polymer Systems

### Markets/Applications



#### Agriculture and Heavy Equipment

Resistance to fading from environmental exposure, as well as protection from fertilizers, pesticides and other chemicals, make these polymers perfect for combines, tractors and other large farm machinery. Another added benefit is a higher tolerance toward cracking under vibrational loads. Enhanced polyolefins can be applied to a variety of applications including roof, hood, fender and other body panels.



#### RV, Heavy Truck and Bus

Enhanced polyolefins are suitable for large transportation applications such as heavy trucks, buses and RVs. Side and roof panels, bumper covers, fender skirts, AC shrouds, propane tank covers, nose cones and interior decorative finishes are just some of the many applications in this market.



#### Power Sports

Snowmobiles, ATVs, jet skis and motorcycles are all perfect applications for enhanced polyolefins which are not only impact-resistant, flexible, durable and ductile under sub-zero temperatures but also lightweight and fade-resistant. Side panels, wheel covers, hood panels and other areas are a great fit for these polymers.



#### Industrial Components

Stiffness, ductility and resistance to weather, chemicals, stress and vibrational cracking make enhanced polyolefins ideal for shrouds, housings and panels in high abuse environments.



#### Personal Watercraft

Power and pontoon boats along with kayaks all benefit from enhanced polyolefins which are lightweight, durable and can withstand constant environmental exposure. Applications can range from interior consoles and headliners to rail skirts and storage compartments.



#### Lawn and Garden

Personal use lawn and garden equipment, such as mowers and garden tractors, gains added resistance from chipping, cracking and bubbling by using enhanced polyolefins. These polymers are ideal for applications like wheel wells, vehicle hoods and body panels.



#### Automobile

Enhanced polyolefins with impact resistance, extreme durability, flexibility and ductility are the superior material for exterior and interior auto applications. LyondellBasell's Color Technology Center has the capability to match a variety of colors in the auto market and provides a wide selection from solids to pearlescent and metallic. Applications include bumper fascias, rocker panels and other decorative finishes.

# Select the LyondellBasell Capstock Grade That's Right for You

These capstock resins provide many exciting benefits in performance and appearance with a broad range of gloss levels depending on your application requirements



|   |          |                       | Capstock Grades                                |                                       |                                   |   |   |
|---|----------|-----------------------|--|---------------------------------------|-----------------------------------|---|---|
|   |          |                       | <i>Polytrope STR</i>                           | <i>Polytrope STR</i>                  | <i>Sequel</i>                     | <i>Polytrope STR</i>                                | <i>Hifax</i>                                  |
| Properties  | Method   | Units                 | 3035EU-01 UV Natural                           | 3571EU-01 UV Natural                  | E1500HG UV NAT                    | 3566EU-01 UV Natural                                | ETA4161 UV NAT                                |
| <b>GENERAL</b>  |          |                       |  |                                       |                                   |   |   |
| Melt Flow Rate (230°C, 2.16 kg)                       | ISO 1133 | g/10 min              | 0.4  | 3.9                                   | 2.0                               | 2.5   | 0.5   |
| Specific Gravity                                      | ISO 1183 | --                    | 1.06   | 0.92                                  | 0.90                              | 0.90  | 0.91  |
| Hardness  | ISO 868  | Shore D               | 74   | 70                                    | 70                                | 74  | 70  |
| <b>THERMAL</b>  |          |                       |  |                                       |                                   |   |   |
| Heat Deflection Temperature                           | ISO 75   |                       |  |                                       |                                   |   |   |
| @ 0.45 MPa  |          | °C                    | 75   | 76                                    | 72                                | 77  | 80  |
| @ 1.80 MPa  |          | °C                    | 50   | 50                                    | 48                                | 50  | 54  |
| <b>MECHANICAL</b>                                     |          |                       |  |                                       |                                   |   |   |
| Flexural Modulus                                      | ISO 178  | MPa                   | 1900   | 750                                   | 1014                              | 1000  | 1200  |
| Tensile Yield Strength                                | ISO 527  | MPa                   | 24   | 21                                    | 30                                | 24  | 38  |
| Tensile Elogation at Break                            | ISO 527  | %                     | 410  | 510                                   | 500                               | 500   | 250   |
| Gloss Gardner Gloss, 60°, Smooth Sheet, After Forming |          |                       | 2-10   | <20                                   | 85-95                             | 85-95   | 30-40   |
|   |          | <b>Key Attributes</b> | Durable, Low Gloss, Hard Mar Resistant Surface | Excellent Clarity, Low Gloss, Durable | High Gloss Polyolefinic Cap Layer | High Clarity, Gloss, Improved Durability, Non-Blush | Cap Layer To Promote Reduced Stress Whitening |

# Select the LyondellBasell TPO Grade That's Right for You

Offering a broad product portfolio that has been designed to meet property performance balance through a diverse offering of stiffness, impact and thermal expansion properties.

**lyondellbasell**  
Advancing Possible

|                                     |                       |   | Sheet Extrusion Grades   |  |  |   |   |   |   |   |  |  |   |
|-------------------------------------|-----------------------|---|--|--|--|---|---|---|---|---|--|--|---|
|                                     |                       |   | <i>Polytrope STR</i>   | <i>Polytrope STR</i>   | <i>Sequel</i>  | <i>Sequel</i>   | <i>Sequel</i>   | <i>Sequel</i>                           | <i>Polytrope STR</i>  | <i>Polytrope STR</i>  | <i>Polytrope STR</i>                                   | <i>Sequel</i>  | <i>Polytrope STR</i>                      |
| Properties                          | Method                | Units   | 1025EU-01 UV Natural   | 1026EU-01 UV Natural   | E3400 UV NAT   | E3400 N0N UV NAT  | E3200 UV NAT  | E3200 NON UV NAT                        | 1050EU-01 UV Natural  | 1050EP-01 NON UV Natural  | 1060EU-01 UV Natural                                   | E3400FR Natural  | 1025EU-01 UV Natural                      |
| <b>GENERAL</b>                      |                       |   |  |  |  |   |   |   |   |   |  |  |   |
| Melt Flow Rate (230°C, 2.16 kg)     | ISO 1133              | g/10 min  | 1  | 0.7  | 0.7  | 0.65  | 0.75  | 0.75                                    | 0.5   | 0.5   | 0.7  | 1.0  | 0.7                                       |
| Specific Gravity                    | ISO 1183              | --  | 0.99   | 0.99   | 1.12   | 1.12  | 1.08  | 1.08                                    | 1.14  | 1.14  | 1.16   | 1.26   | 1.31                                      |
| Hardness                            | ISO 868               | Shore D   |  | 71   | 67   | 66  | 66  | 66                                      | 68  | 68  | 70   | 65   |   |
| Flame rating type, all colors       |                       | Internal  | HB @ 0.125 in  | HB @ 0.125 in  | HB @ 0.125 in  | HB @ 0.125 in   | HB @ 0.125 in   | HB @ 0.125 in                           | HB @ 0.125 in   | HB @ 0.125 in   | HB @ 0.125 in  | V1 @ 3.0 mm. V0 @ 6.0MM                                | HB @ 0.125 in VO @ 0.0625 in 5VA @ 0.0625 |
| <b>THERMAL</b>                      |                       |   |  |  |  |   |   |   |   |   |  |  |   |
| Heat Deflection Temperature         | ISO 75                |   |  |  |  |   |   |   |   |   |  |  |   |
| @ 0.45 MPa                          |                       | °C  | 94   | 98   | 102  | 95  | 85  | 85                                      | 114   | 114   | 117  | 103  | 91  |
| @ 1.80 MPa                          |                       | °C  |  | 54   | 56   | 52  | 49  | 49                                      | 57  | 57  | 57   | 56   |   |
| CLTE (-30°C to 80°C)                | ASTM E228             | 10 <sup>-5</sup> /°C  | 9.9  |  | 4.8  | 4.0   | 5.5   | 5.5                                     | 4.0   | 4   | 5.4  | 5.3  | 5.4                                       |
| <b>MECHANICAL</b>                   |                       |   |  |  |  |   |   |   |   |   |  |  |   |
| Flexural Modulus                    | ISO 178               | MPa   | 1,725  | 1,650  | 2,100  | 2,250   | 1,450   | 1,450                                   | 2,400   | 2,400   | 3,000  | 2,400  | 2,100                                     |
| Tensile Yield Strength              | ISO 527               | MPa   | 21   | 26   | 21   | 22  | 21  | 21                                      | 24  | 24  | 27   | 20   | 19  |
| Tensile Elongation at Break         | ISO 527               | %   | >200   | >500   | >200   | >500  | >500  | >500                                    | 300   | 300   | 175  | >150   | 430                                       |
| <b>IMPACT</b>                       |                       |   |  |  |  |   |   |   |   |   |  |  |   |
| Izod Impact Strength                | ISO 180               |   |  |  |  |   |   |   |   |   |  |  |   |
| @ 23°C (73°F)                       |                       | kJ/m <sup>2</sup>   | 82   | 54   | 82   | 64  | 67  | 67                                      |   |   |  | 38   |   |
| @ -30°C (-22°F)                     |                       | kJ/m <sup>2</sup>   | 7  | 4  | 7  | 6.5   | 4.8   | 4.8                                     |   |   |  | 4  |   |
| Multi-Axial Impact (2.2 m/s) -15°C  | ASTM D3763            |   |  |  |  |   |   |   |   |   |  |  |   |
| Total Energy                        |                       | J   |  | 17   | 51   | 48  | 40  | 40                                      | 44  | 44  |  | 26   | 35  |
| Failure Mode (D-Ductile; B-Brittle) |                       | D/B   |  | 100% brittle   | 100% ductile   | 100% ductile  | partially ductile   | partially ductile                       | 100% ductile  | 100% ductile  |  | partially ductile                                      | 100% ductile                              |
| Multi-Axial Impact (2.2 m/s) -30°C  | ASTM D3763            |   |  |  |  |   |   |   |   |   |  |  |   |
| Total Energy                        |                       | J   | 47.4   |  | 57   | 39  | 28  | 28                                      |   |   |  | 37   |   |
| Failure Mode (D-Ductile; B-Brittle) |                       | D/B   | 100% D   |  | 100% ductile   | 100% ductile  | brittle   | brittle                                 |   |   |  | brittle  |   |
|                                     | <b>Key Attributes</b> | For Applications requiring lower stiffness and high impact. | For applications requiring lower stiffness . Commercially approved for Automotive trim applications. | Excellent balance of high stiffness and high impact; improved melt strength for thermoforming. | Excellent balance of high stiffness and high impact; improved melt strength for thermoforming. Adjusted for full paint applications. | Adjusted for cost sensitive applications requiring less impact and Thermoformability. | Adjusted for cost sensitive applications requiring less impact and Thermoformability. Modified for full paint applications. | Designed for High Modulus and Toughness | Designed for High Modulus and Toughness, Modified for Full paint applications | Balances toughness and exceptional high stiffness and Low Temperature impact. | For applications requiring UL 94 V-1 flame retardancy. | For applications requiring UL 94 V-0 flame retardancy. |   |

# Select the Weatherable Polymer Systems That's Right for You

Our broad portfolio of ABS, ASA, ASA/PC and ASA/AES polymers can be customized to fit your sheet extrusion and thermoforming processes.



|   |               |            |                       | Co-Extrusion Sheet Grades          |                                      |                                      |                                    |                                 |                                     |
|---|---------------|------------|-----------------------|------------------------------------|--------------------------------------|--------------------------------------|------------------------------------|---------------------------------|-------------------------------------|
| Properties                                    | ASTM Standard | Units      | Conditions            | Centrex                            | Centrex                              | Centrex                              | Centrex                            | Diamond                         | Diamond                             |
|   |               |            |                       | 485 CS                             | 825A                                 | 833A                                 | ST4800                             | 9501-1001S                      | 9501                                |
| <b>GENERAL</b>                                |               |            |                       |                                    |                                      |                                      |                                    |                                 |                                     |
| Resin Type                                    |               |            |                       | ASA - Low Gloss                    | ASA -High Gloss                      | ASA / AES                            | ASA / TPE                          |                                 |                                     |
| Melt Flow Rate                                | D 1238        | g/10 min   | 200°C, 5 kg           | N/A                                | N/A                                  | N/A                                  | N/A                                | 0.40 to 1.2 g/10 min            | 0.40 g/10 min                       |
| Melt Flow Rate                                | D 1238        | g/10 min   | 220°C, 10 kg          | 5                                  | 12                                   | 10                                   | N/A                                | N/A                             | N/A                                 |
| Melt Flow Rate                                | D 1238        | g/10 min   | 230°C, 3.8 kg         | 1.5                                | 3.5                                  | 1.8                                  | 15                                 | N/A                             | N/A                                 |
| <b>THERMAL</b>                                |               |            |                       |                                    |                                      |                                      |                                    |                                 |                                     |
| Vicat   | D 1525        | °F         | 1 kg, 120°C/hr        | 212                                | 215                                  | 195                                  | N/A                                | 221                             | 284                                 |
| Deflection Temperature under Load, Unannealed | D 648         | °F         | 66 psi, 0.125"        | 188                                | 198                                  | 185                                  | N/A                                | 195                             | 253                                 |
| Deflection Temperature under Load, Unannealed | D 648         | °F         | 264 psi, 0.125"       | 155                                | 172                                  | 160                                  | N/A                                | 168                             | 223                                 |
| <b>MECHANICAL</b>                             |               |            |                       |                                    |                                      |                                      |                                    |                                 |                                     |
| Tensile Modulus                               | D 638         | psi        | 73°F, 0.2 in/min      | 210,000                            | 330,000                              | 295,000                              | N/A                                | N/A                             | N/A                                 |
| Tensile Stress at Yield                       | D 638         | psi        | 73°F, 0.2 in/min      | 3,850                              | 6,400                                | 5,100                                | N/A                                | 6,240                           | 6,070                               |
| Tensile Stress at Break                       | D 638         | psi        | 73°F, 0.2 in/min      | 2,285                              | 4,800                                | 4,100                                | N/A                                | 4,930                           | N/A                                 |
| Tensile Elongation at Break                   | D 638         | %          | 73°F, 0.2 in/min      | 50                                 | 36                                   | 35                                   | N/A                                | 20                              | N/A                                 |
| Flexural Modulus                              | D 790         | psi        | 73°F, 0.05 in/min     | 200,000                            | 305,000                              | 250,000                              | N/A                                | 333,000                         | 317,000                             |
| Flexural Stress at Yield                      | D 790         | psi        | 73°F, 0.05 in/min     | 50,600                             | 7,800                                | 7,500                                | N/A                                | N/A                             | N/A                                 |
| <b>IMPACT</b>                                 |               |            |                       |                                    |                                      |                                      |                                    |                                 |                                     |
| Izod Notched Impact Strength                  | D 256         | ft - lb/in | 73°F, 0.125"          | 2.5                                | 2.5                                  | 9                                    | N/A                                | 9.7                             | 2.9                                 |
| Hardness                                      | D 785         | scale      |                       | 97 R                               | 104 R                                | 89 R                                 | 46 D                               | 101                             | 104                                 |
| Instrumented Impact, Total Energy             | D 3763        | joules     | 73°F, 0.125"          | 24                                 | 38                                   | 43                                   | 8                                  | N/A                             | N/A                                 |
| Instrumented Impact, Total Energy             | D 3763        | joules     | -30°F                 | 6                                  | 12                                   | 30                                   | N/A                                | N/A                             | N/A                                 |
| Specific Gravity                              | D 792         |            | 23°C                  | 1.06                               | 1.05                                 | 1.05                                 | 1.08                               | 1.04                            | 1.07                                |
| Gloss, Sheet/Profile*                         | D 523         |            | 60°                   | 20                                 | 95                                   | 95                                   | 10                                 | N/A                             | N/A                                 |
| Gloss, Formed Sheet*                          | D 523         |            | 60°                   | 10                                 | 90                                   | 90                                   | 8                                  | N/A                             | N/A                                 |
|   |               |            | <b>Key Attributes</b> | Low Gloss<br>10 @ at 60<br>degrees | High Gloss<br>90+ @ at 60<br>degrees | High Gloss<br>90+ @ at 60<br>degrees | Low Gloss<br>10 @ at 60<br>degrees | Ultra High Impact<br>Resistance | Ultra High<br>Impact<br>Restistance |

\* Gloss data will vary with processing conditions.

# ABOUT US

**LyondellBasell (NYSE: LYB)** is one of the largest plastics, chemicals and refining companies in the world. Driven by its employees around the globe, LyondellBasell produces materials and products that are key to advancing solutions to modern challenges like enhancing food safety through lightweight and flexible packaging, protecting the purity of water supplies through stronger and more versatile pipes, improving the safety, comfort and fuel efficiency of many of the cars and trucks on the road, and ensuring the safe and effective functionality in electronics and appliances. LyondellBasell sells products into more than 100 countries and is the world's largest producer of polymer compounds and the largest licensor of polyolefin technologies. More information about LyondellBasell can be found at [www.LyondellBasell.com](http://www.LyondellBasell.com).

Before using a product sold by a company of the LyondellBasell family of companies ("LyondellBasell"), users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. LyondellBasell MAKES NO WARRANTY, EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) OTHER THAN AS AGREED TO BY LyondellBasell IN THE PRODUCT SALE CONTRACT.

LyondellBasell prohibits or restricts the use of its products in certain applications. For further information on restrictions or prohibitions of use, please contact a LyondellBasell representative.

Users should review the applicable Safety Data Sheet before handling the product.

*Polytrope, Sequel, Hifax, Polytrope STR, Centrex and Diamond* are trademark owned and/or used by the LyondellBasell family of companies and they are registered in the U.S. Patent and Trademark Office.

**lyondellbasell**  
*Advancing Possible*